



AMENDMENTS TO THE CLAIMS

1. (twice amended) A mixture comprising at least one compound of the formula (I)




where R¹ is hydrogen, C₁-C₄-alkyl, halogen, or C₁-C₄-alkoxy,

n is 1 or 2, and the

ring A is optionally substituted with C₁-C₄-alkyl or halogen,

and at least one compound of the formula (II)



where X is halogen, or CN,



R² and R⁵ are independently hydrogen or C₁ -C₄ -alkyl, and

R³ and R⁴ are independently hydrogen, [optionally substituted C₁ -C₄ -alkyl or] C₂ -C₄ -alkenyl, unsubstituted C₁ -C₄ -alkyl or a NC-substituted C₁ -C₄ -alkyl, H₅C₆-substituted C₁ -C₄ -alkyl, C₁-C₄ alkoxy substituted C₁ -C₄ -alkyl or ROOC- substituted C₁-C₄ alkyl, and wherein R is hydrogen or C₁ -C₄ -alkyl.


2. The mixture of claim 1, comprising at least one compound of the formula (I) where the ring A does not bear any further substituents.
3. The mixture of claim 1, comprising at least one compound of the formula (I) where R¹ is hydrogen or C₁ -C₄ -alkyl.
4. The mixture of claim 1, comprising at least one compound of the formula (I), where n is 1, R¹ is hydrogen or methyl and the ring A is not further substituted.
5. The mixture of claim 1, comprising compounds of the formula (II) where X is halogen.
- [6. The mixture of claim 1, comprising compounds of the formula (II) where R³ and R⁴ are independently hydrogen, C₂ -C₄ -alkenyl, unsubstituted C₁ -C₄ -alkyl or

ROCO--, NC-- and/or ROOC-substituted C₁ -C₄ -alkyl, R being hydrogen or C₁ -C₄ -alkyl.]

7. The mixture of claim 1, comprising a compound of the formula (III), (IV) and/or (V)



and/or



where X¹ is halogen or CN,

X² is halogen, hydrogen, NO₂ or CN,

R⁶ is C₁ -C₄ -alkyl,

R⁷ and R⁸ are independently hydrogen, unsubstituted or HO-, NC-, ROCO-, H₅C₆OCO-,

(C₁ -C₄ -alkyl)OOCO-, ROOC-, H₅ C₆ O-, H₅ C₆- and/or C₁ -C₄-alkoxy-substituted C₁ -C₄ -alkyl and/or C₂ -C₄ -alkenyl, R being hydrogen or C₁ -C₄ -alkyl,
Y¹ and Y² are independently hydrogen or halogen,
R⁹ and R¹⁰ are independently hydrogen, unsubstituted or HO-, NC-, ROCO-, H₅C₆OCO- and/or C₁ -C₄ -alkoxy-substituted C₁ -C₄ -alkyl, R being as defined above, or C₂ -C₄ -alkenyl,
R¹¹ is C₁ -C₄ -alkyl, and
R¹² is hydrogen, C₁ -C₄ -alkyl or C₁ -C₄ -alkoxy.

8. (Twice amended) The [mixtures] mixture of claim 1, comprising 1 to 99% by weight[, especially 1 to 80% by weight,] of at least one compound of the formula (I) and 1 to 99% by weight, [especially 20 to 99% by weight,] of at least one compound of the formula (II), based on total amount of dye.
9. A dye preparation comprising
10 to 60% by weight of dye mixture according to claim 1, and
40 to 90% by weight of dispersant.
10. (Once amended) A process for producing the dye preparation of [claim 8] claim 9, in which the individual dyes of the dye mixture of claim 1 are ground in water in the presence of a dispersant, then mixed and optionally dried or in which the dye mixture of claim 1 is ground in water in the presence of a dispersant and optionally dried.
11. A method for dyeing and printing hydrophobic synthetic materials or for mass coloration of hydrophobic synthetic materials in which the dye mixture of claim 1 is used.
12. The hydrophobic synthetic material dyed or printed with the dye mixture of claim 1.

(Once amended) 13. The mixture of claim 1, comprising 1 to 80% by weight of at least one compound of the formula (I) and 20 to 99% by weight of at least one compound of the formula (II), based on total amount of dye.

(Once Amended) 14. A process for producing the dye preparation of claim 9, in which the individual dyes of the dye mixture are ground in water in the presence of a dispersant, then mixed and optionally dried or in which the dye mixture of is ground in water in the presence of a dispersant and optionally dried wherein the mixture comprises 1 to 99% by weight of at least one compound of the formula (I) and 1 to 99% by weight of at least one compound of the formula (II), based on total amount of dye.

(Once Amended) 15. A process for producing the dye preparation of claim 9, in which the individual dyes of the dye mixture of are ground in water in the presence of a dispersant, then mixed and optionally dried or in which the dye mixture of is ground in water in the presence of a dispersant and optionally dried wherein the mixture comprises 1 to 80% by weight of at least one compound of the formula (I) and 20 to 99% by weight of at least one compound of the formula (II), based on total amount of dye.

16. The mixture of claim 1, comprising 5 to 60% by weight of at least one compound of the formula (I) and 40 to 95% by weight of at least one compound of the formula (II), based on total amount of dye.

17. The mixture of claim 1, comprising compounds of the formula (II) where R^3 and R^4 are independently C_2 - C_4 -alkenyl or unsubstituted C_1 - C_4 -alkyl.

18. The mixture of claim 16, comprising compounds of the formula (II) where R^3 and R^4 are independently C_2 - C_4 -alkenyl or unsubstituted C_1 - C_4 -alkyl.

19. A process for producing the dye preparation of claim 9, in which the individual dyes of the dye mixture of are ground in water in the presence of a dispersant, then mixed and optionally dried or in which the dye mixture of is ground in water in the presence of a dispersant and optionally dried wherein the mixture comprises 5 to 60% by weight of at least one compound of the formula (I) and 40 to 95% by weight of at least one compound of the formula (II), based on total amount of dye.
20. The process of claim 19, wherein R³ and R⁴ are independently C₂-C₄-alkenyl or unsubstituted C₁-C₄-alkyl.